



## **APPLICATION DATA SHEET**

### **Blackfast 551 Conditioner**

**USE:** 10% solution in water.

**APPLICATION:** For use on hardened steels and cast iron especially mild steel, the use of Blackfast Conditioner results in a homogenous surface ready for blacking. After degreasing (and pickling if necessary) steels are clean but usually exhibit surface variations which, if not treated, can result in uneven blacked surfaces. Immersion for 30-60 seconds in a 10% solution of Blackfast Conditioner in water, prepares the surface so that consistent blacking is achieved. Immersion for a longer period is not recommended since over-conditioning leads to inconsistent blacking and patchy results.

**TANK MATERIAL:** Tanks should be of a suitable polypropylene.

**PRODUCT SAFETY DATA SHEET:** A safety data sheet is available

Blackfast Conditioner is part of the Blackfast Australia range of products for the chemical blacking of iron and steel at room temperature.

Blackfast Australia continues to improve the quality and performance of its range of products and reserves the right to modify product formulations without prior notice.

April 23